

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 October 2003 (02.10.2003)

PCT

(10) International Publication Number
WO 03/080692 A1

(51) International Patent Classification⁷: **C08F 297/04**,
C09J 153/02, C08L 53/02

(74) Agents: **BEETZ**, Tom et al.; De Vries & Metman, Over-
schiestraat 180, NL-1062 XK Amsterdam (NL).

(21) International Application Number: **PCT/EP03/03172**

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 24 March 2003 (24.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02076178.9 26 March 2002 (26.03.2002) EP

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **KRATON POLYMERS RESEARCH B.V.** [NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(72) Inventors; and

(75) Inventors/*Applicants*: **VERMUNICHT, Geert, F.** [NL/NL]; Monnet 1, Ottignies, B-1348 Louvain-la-Neuve (NL); **DE VLIET, Birgitte, M.** [NL/NL]; Monnet 1, Ottignies, B-1348 Louvain-la-Neuve (NL); **SOUTHWICK, Jeffrey, G.** [US/US]; 1811 Laguna Meadows Lane, Houston, TX 77094 (US).

(54) Title: **POLY (STYRENE-BUTADIENE-STYRENE) POLYMERS HAVING A HIGH VINYL CONTENT IN THE BUTADIENE BLOCK AND HOT MELT ADHESIVE COMPOSITIONS COMPRISING SAID POLYMERS**

(57) Abstract: The present invention concerns a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block comprising in combination a polystyrene content (PSC) within a range of 15-20 % by weight, a coupling efficiency (CE) of 50-80 %, a step I molecular weight (MW) between 9,000 and 10,000 kg/mol, and a vinyl content between 20-45 %. Hot melt adhesive compositions are also described comprising said SBS polymer together with a tackifying resin, a plasticizer and an anti-oxidant.

WO 03/080692 A1

POLY(STYRENE-BUTADIENE-STYRENE) POLYMERS HAVING A HIGH VINYL CONTENT IN THE BUTADIENE BLOCK AND HOT MELT ADHESIVE COMPOSITION COMPRISING SAID POLYMERS

Summary of the invention

The present invention comprises a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block for packaging tape adhesives and a hot melt polymer adhesive composition comprising said poly(styrene-butadiene-styrene) polymers (SBS).

More particularly the present invention concerns a hot melt adhesive composition having equal or better properties compared to emulsion acrylic tapes. The adhesive composition of the present invention has excellent tack, adhesive strength, creep resistance and also an excellent treatment capability at high temperature and high box closing properties.

The adhesives of the present invention are suitable for adhesion tapes, labels, pressure sensitive sheets, tacky adhesives for fixing carpets etc.

The advantages of the adhesives of the present invention are that they are lower in cost compared to emulsion acrylic based adhesives or poly(styrene-isoprene-styrene) based adhesives (SIS) while having comparable or better properties.

Background of the Invention

Hot melt adhesives are known, for instance, in the JP 2001787 describing tacky adhesive compositions for tapes comprising a block copolymer of a vinylaromatic hydrocarbon and a high vinyl polybutadiene block. The composition comprises a block copolymer, a tackifying resin and at least one phenol compound. The block

copolymer is composed of at least one polymeric block mainly containing butadiene. It has a vinylaromatic hydrocarbon content of 10-36% by weight and the butadiene portions have a vinyl content of 15-55%.

The JP 63182386 discloses sticky block copolymer compositions containing a vinyl aromatic-butadiene block copolymer, a tackifying resin and a phenolic compound. The block copolymer is mainly composed of vinyl aromatic hydrocarbon and at least one polymer block composed of polybutadiene.

The EP-A-0 243 956 discloses an adhesive composition comprising a block copolymer containing at least one vinylaromatic hydrocarbon block and one butadiene containing block, wherein the relationship between the vinylaromatic hydrocarbon block and the 1,2-vinyl content in the butadiene portion is within a ratio between 40 and 70. In addition, the polymers that have been used have a melt flow rate of 5 g/10 min (at 300 °C, 1 kg).

These hot melt compositions however do not have the same properties as those based on SIS in respect of the tack, adhesive strength creep resistance and treatment capacity at high temperature as well as high box closing properties.

The object of the invention is a hot melt adhesive composition having equal or better properties compared to prior art adhesives, especially the acrylic emulsion based adhesives while being cheaper than poly(styrene-isoprene-styrene) (SIS) based adhesives.

Poly(styrene-isoprene-styrene) polymers are currently rarely used in pressure sensitive adhesives despite their relative low cost. The main reason for this is their high viscosity and tendency to cross-link so that the processing step becomes a limiting factor.

Surprisingly a new SBS polymer has been developed with molecular parameters suitable for hot melt adhesive applications.

Brief description of the invention

Accordingly, the inventors have provided a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block comprising in combination :

- i) a polystyrene content (PSC) within a range of 15-20% by weight,
- ii) a coupling efficiency of 50-80%,
- iii) a step I molecular weight (MW) between 9,000 and 10,000 kg/mol
- iv) a vinyl content between about 20-45% by weight.

Further the inventors have provided a hot melt adhesive composition comprising:

- a) a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block
- b) a tackifying resin
- c) a plasticizer
- d) an anti-oxidant

wherein said polymer has :

- i) a polystyrene content (PSC) within a range of 15-20% by weight,
- ii) a coupling efficiency (CE) of 50-80%,
- iii) a step I molecular weight (MW) between 9,000 and 10,000 kg/mol
- iv) a vinyl content between about 20-45% by weight.

Detailed description of the invention

Preferred poly(styrene-butadiene-styrene) polymers having a high vinyl content in the butadiene block have a polystyrene content between 16-19% by weight, more preferably 16-18%. Likewise the preferred polymers have a

coupling efficiency between 60-75%, more preferably 65-70%. Moreover the preferred polymers have a vinyl content between 25-40% by weight, more preferably 30-35.

A suitable embodiment of the present invention is defined as follows:

PSC content (%)	16
CE (%)	67
vinyl (%)	33.6
Step I MW (kg/mol)	9,100

According to another embodiment of the present invention the polymer is defined as follows:

PSC content (%)	18
CE (%)	67
vinyl (%)	32
Step I MW (kg/mol)	9,100

Suitable styrenes useful for preparing the polystyrene blocks of the SBS of the present invention are for example styrene, o-methylstyrene, p-methylstyrene, m-methylstyrene, p-tert-butylstyrene, dimethylstyrene, and various other alkyl-substituted styrenes, alkoxy-substituted styrenes vinyl naphthalene and vinyl xylene. The alkyl and alkoxy groups of the alkyl-substituted or alkoxy-substituted styrenes respectively preferably contain from 1 to 6 carbon atoms, preferably from 1 to 4 carbon atoms. It is to be noticed that this list is merely illustrative and should not have a limiting effect. The polystyrene blocks may comprise minor amounts (e.g. up to 5% by weight) of copolymerizable monomers.

In the preparation of the polymers according to the invention any suitable difunctional coupling agent can be used. Alternatively, the same polymer may be produced by what is called "full sequential". This is also within the scope of this invention.

The coupling agent may (not preferred) be a multifunctional coupling agent. Suitable coupling agents are dibromo ethane diglycidyl ether of bisphenol A and such like components as known in the art.

Suitable tackifiers for preparing the hot melt adhesive composition of the present invention are well-known in the art. They may for example, be selected from the group consisting of compatible C₅ hydrocarbon resins, hydrogenated C₅ hydrocarbon resins, styrenated C₅ resins, C₅/C₉ resins, styrenated terpene resins, fully hydrogenated or partially hydrogenated C₉ hydrocarbon resins, rosins esters, rosins derivatives and mixtures thereof.

The composition according to the present invention preferably comprises from 50 to 200 parts by weight, more preferably from 100 to 150 parts by weight of a tackifier.

The preferred tackifying resins useful in the present invention are selected within the group of HERCOTAC 205 (trademark), an aromatic modified hydrocarbon resin of the Hercules grade range, used for natural rubber based packaging tapes; PICCOTAC 212 (trademark) a purely aliphatic resin widely used in hot melt pressure sensitive adhesives; MBG 223, a Hercules development grade which is a 35% aromatic modified C₅ resin, developed for tackifying SBS based adhesives; MBG 264, a partially hydrogenated hydrocarbon resin used in radiation curable adhesives based on SBS; and A 2514 which is a liquid developmental resin, with a very low softening point to be used in combination with a solid resin to increase the tack properties.

Suitable plasticizers for use in preparing the hot melt adhesive compositions of the present invention

include plasticizing oils like low aromatic content hydrocarbon oils that are paraffinic or naphthenic in character (carbon aromatic distribution $\leq 5\%$, preferably $\leq 2\%$, more preferably 0% as determined according to DIN 51378). Those products are commercially available from the Royal Dutch/Shell Group of companies, like SHELLFLEX, CATENEX, and ONDINA oils. Other oils include KAYDOL oil from Witco, or TUFFLO oils from Arco. Other plasticizers include compatible liquid tackifying resins like REGALREZ R-1018. (SHELLFLEX, CATENEX, ONDINA, KAYDOL, TUFFLO and REGALREZ are trademarks).

Other plasticizers might also be added, like olefin oligomers; low molecular weight polymers ($\leq 30,000$ g/mol) like liquid polybutene or liquid polyisoprene copolymers, like liquid styrene/isoprene copolymers or hydrogenated styrene/isoprene copolymers and liquid alpha-olefin polymers; vegetable oils and their derivatives; or paraffin and microcrystalline waxes.

The preferred plasticizers useful in the present invention are for example, CATENEX N956, CATENEX S946, or EDELEX 945.

The composition according to the present invention may, but need not, contain a plasticizer. If it does, then the composition comprises up to 100 parts by weight, preferably 5 to 75 parts by weight, more preferably 10 to 40 parts by weight of a plasticizer.

Several types of antioxidants can be used, either primary antioxidants like hindered phenols or secondary antioxidants like phosphite derivatives or blends thereof. Examples of commercially available antioxidants are IRGANOX 565 from Ciba-Geigy (2,4-bis-(n-octylthio)-6-(4-hydroxy-3,5-di-tertiary-butyl anilino)-1,3,5-triazine), IRGANOX 1010 from Ciba-Geigy (tetrakis-ethylene-(3,5-di-

tertiary-butyl-4-hydroxy-hydrocinnamate)methane), IRGAFOS 168 from Ciba-Geigy or POLYGARD HR from Uniroyal (tris-(2,4-di-tertiary-butyl-phenyl)phosphite). Other antioxidants developed to protect the gelling of the polybutadiene segments can also be use, like the SUMILIZER GS from Sumitomo (2[1-(2-hydroxy-3,5-di-ter-pentylphenyl)-ethyl])-4,6-di-tert-pentylphenylacrylate); SUMILIZER T-PD from Sumitomo (pentaerythrythyltetrakis(3-dodecylthiopropionate)); or mixtures thereof. (IRGANOX, IRGAFOS, POLYGARD and SUMILIZER are trademarks).

The antioxidant which can be used in the present invention are IRGANOX 1010, IRGANOX 3052, IRGAFOS 168, SUMILIZER GS, SUMILIZER TPD. Extensive research has revealed that optimized antioxidant packages are a combination of IRGANOX 1010/IRGANOX 3052/IRGAFOS 168 or a combination of SUMILIZER GS/SUMILIZER TPD which gave stable hot melts at 180°C.

It should be noted that the lists of additives disclosed herein above are merely examples and are not limitative.

Test methods have been performed on the adhesives in order to evaluate those of the present invention which are able to compete with acrylic tapes.

These tests are:

1) Hot melt viscosity stability

Brookfield hot melt viscosity (HMV) at 170°C during 24 hours

2) Gel content

Gel content on adhesive before (ini) and after HMV measurement (24 h) on 50 µ filter

3) Tack property

Rolling Ball Tack (RBT)

4) Test on cardboard

HP 40°C, 1 kg weight

Flap test, 500 g weight

These tests have shown that in order to attain the object of the present invention, the adhesive composition of (poly(styrene-butadiene-styrene) polymers having a high vinyl content in the butadiene blocks based packaging tapes) ideally should fulfill the following requirements:

RBT:	1-5 cm	(acceptable < 20 cm)
Flap test:	120-250 minutes	(acceptable > 100 minutes)
HP 40°C:	50-100 minutes	(acceptable > 40 minutes)
HMV	< 100 Pa.s.	

The tests have been performed with the following polymers A to H, whereby A to F are comparative examples while G and H are embodiments of the present invention.

Table 1

	A	B	C	D	E	F*	G	H
Step I (mol/kg)	11,300	11,800	11,100	11,600	11,100	10,004	9,100	9,100
Step III (mol/kg)	193,000	223,800	205,300	222,900	199,800	188,400	182,100	175,200
CE (%)	65.5	82.6	53.8	17.6	23	79	67	67
vinyl (%)	40.5	7.6	36	9.2	55	30	32	33.6
PSC (%)	18.7	17.9	17.9	17.5	18.8	19	18	16
MFR 200°C, 5 kg	3.0					5	14	10

* An example in accordance with EP 0 243 956

The properties are shown in Table 2. In that table, the formulation 1 is a general formulation.

Table 2

Polymer	A	B	C	D	E
Form. 1					
HMV@170, Pa.s	57	198	51	26	33
RBT (cm)	15	3	6	1	21
HP kraft@40°C, min	41	8	9	2	4
Flap kraft@23°C, min	548	118	82	22	148

Form. 1 = 100 phr SBS polymer / 125 phr HERCOTAC 205 / 40 phr CATENEX N956 / 1 phr IRGANOX 1010 / 1 phr IRGANOX 3052/1 phr IRGAFOS 168

It is to be pointed out that in the formulation 1 the amount of the plasticizer CATENEXTM N 956 (40 phr) is too high and this causes bleeding and migration of the adhesive.

Although the formulation based on polymer A exhibits an acceptable balance of properties, this formulation is not acceptable as polymer A has a too low melt flow rate (MFR < 10).

Since formulations with lower oil contents are preferred, for example below 20 phr, polymers with lower step I (MW) have been compared to polymers A to E. These polymers are F, G and H in table 1 and the characteristics of these polymers are indicated in that table 1.

Table 3

In another text a formulation 2 is prepared with the SBS polymers F and G, but containing only 20 phr of the plasticizer CATENEX™ N 956.

Form 2: 100 phr SBS polymer / 125phr HERCOTAC™ 205 / 20 phr CATENEX™ N956 / 1phr IRGANOX™ 1010 / 1phr IRGANOX™ 3052 / 1phr IRGAFOS™ 168

The results of the text are shown hereunder.

	F	G
HMV@170, Pa.s	190	63
RBT (cm)	5	27
HP kraft@40°C, min	51	19
Flap kraft@23°C, min	708	135

It will be seen that F, having a maximum step I MW of more than 10,000, a maximum coupling efficiency value of 79% and a MFR of 5, results in a far too high HMV (hot melt viscosity) for a packaging tape formulation rendering it hardly processable so that G is the polymer with the best balance of properties.

It should be pointed out that the properties of the adhesives could be further improved in optimizing the formulation. The most suitable molecule is specified by the parameters hereunder which result in a MFR of 10. The target molecule has the following characteristics:

Step I (kg/mol)	9,400-9,600, preferably about 9,500
vinyl (%)	25-40, preferably about 30
PSC (%)	16-19, preferably about 19
CE (%)	60-75, preferably about 70

In the following tables, examples are shown where one can see how the properties of the adhesive composition can be altered by changing the amounts of the several additives. In table 4 has been used the polymer G and in table 5 has been used the polymer H.

Table 4

Ingredients	F1A	F1B	F2A	F2B	F3	F4
Polymer G	100	100	100	100	100	100
HERCOTAC 205	125	125	83	83	94	-
PICCOTAC 212	-	-	42	42	46	-
MBG223	-	-	-	-	-	140
CATENEX N956	20	20	20	20	30	30
I1010/I3052/I168	3*1	3*1	3*1	3*1	3*1	3*1
Coating weight, μ	17	24	18	25	18	20
BMV, 170°C, (ini) Pa.s	63	63	61	61	40	40
BMV, min	27	5.5	>30	>30	>30	7
BMV, 40°C, min	19	27	31	55	30	31
Flap kraft@23°C, min	135	230	308	681	221	179

3*1 means 1/1/1

Table 5

	F1	F2	F4	F5	F6	F7
Polymer H	100	100	100	100	100	100
HERCOTAC 205	125	105	112.5	100	125	125
PICCOTAC 212	-	-	12.5	25	-	-
CATENEX N956	20	15	20	20		
CATENEX S946					20	
EDELEX 945						20
I1010/I168/I3052	3*1	3*1	3*1	3*1	3*1	3*1
Coating weight, μ	18	18	20	20	19	19
HMV(ini), 170°C, Pa.s	100	120	100	90	100	80
RBT, cm	29	24	24	30	15	25
HP kraft@40°C, min	26	36	39	31	37	33
Flap kraft@23°C, min	217	239	311	383		239

It is seen in Table 4 that the compositions F1F₄ furnish very valuable adhesives falling within the limits of properties desired for the adhesives of the present invention.

Various changes can be made in the above compositions, and products without departing from the scope of the appended claims.

C L A I M S

1. Poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block comprising in combination

i) a polystyrene content (PSC) within a range of 15-20% by weight

ii) a coupling efficiency (CE) of 50-80%

iii) a step I molecular weight (MW) between 9,000 and 10,000 kg/mol

iv) a vinyl content between 20-45%

2. The polymer according to claim 1 wherein the polystyrene content (PSC) is within a range of 16-19% by weight, preferably 16-18% by weight.

3. The polymer according to claim 1 wherein the coupling efficiency is within a range of 60-75%, preferably 65-70%.

4. The polymer according to claim 1 wherein the vinyl content amounts to 25-40% preferably 30-35 by weight.

5. Hot melt adhesive composition comprising:

a) a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block according to any one of claims 1-4;

b) a tackifying resin;

c) a plasticizer; and

d) an anti-oxidant.

6. The hot melt adhesive composition according to claim 5 characterized in that said polymer has the following characteristics

Polystyrene (PSC) content (%)	16-19, preferably about 19
CE (%)	60-75, preferably about 70
Step I MW (kg/mol)	9,400-9,600, preferably about 9,500; and

Vinyl (%) 25-40, preferably about 30.

7. The hot melt adhesive composition according to any one of claims 5 to 6 having

a) hot melt viscosity at 170°C during 24 hours lower than 100 Pa.S

b) Rolling back tack: 1-5 cm

c) Flap test, 500 g weight: higher than 120 minutes

d) HP 40°C, 1 kg weight: higher than 50 minutes.

8. The hot melt adhesive composition according to anyone of claims 5-7 wherein the amount of tackifier in the composition comprises 50 to 200 parts by weight, preferably 100 to 150 parts.

9. The hot melt adhesive composition according to anyone of claims 5-8 wherein the amount of plasticizer in the composition is up to 100 parts by weight, preferably 5 to 75 parts by weight.

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/E /03172

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F297/04 C09J153/02 C08L53/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C09J C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX, IBM-TDB, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 777 039 A (DUPONT MARTINE JEANNE ET AL) 7 July 1998 (1998-07-07) whole document	1-9
Y	US 4 792 584 A (SHIRAKI TOSHINORI ET AL) 20 December 1988 (1988-12-20) whole document	1-9
Y	EP 0 659 781 A (SHELL INT RESEARCH) 23 June 1995 (1995-06-28) whole document	1-9



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

4 July 2003

Date of mailing of the international search report

25/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gold, J

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/E /03172

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5777039	A	07-07-1998	AT 193712 T	15-06-2000
			AU 707164 B2	01-07-1999
			AU 1768097 A	28-08-1997
			BR 9707351 A	27-07-1999
			CA 2245672 A1	14-08-1997
			CN 1210545 A	10-03-1999
			DE 69702240 D1	13-07-2000
			DE 69702240 T2	25-01-2001
			DK 879253 T3	20-11-2000
			WO 9729140 A1	14-08-1997
			EP 0879253 A1	25-11-1998
			ES 2146978 T3	16-08-2000
			GR 3034221 T3	29-12-2000
			HU 9900932 A2	28-07-1999
			JP 2000505483 T	09-05-2000
			PT 879253 T	30-11-2000
			RU 2167166 C2	20-05-2001
			TR 9801505 T2	23-11-1998
			TW 438854 B	07-06-2001
			ZA 9700969 A	13-11-1997
US 4792584	A	20-12-1988	JP 1786154 C	31-08-1993
			JP 4074387 B	26-11-1992
			JP 62257978 A	10-11-1987
			JP 1815606 C	18-01-1994
			JP 4074388 B	26-11-1992
			JP 63027573 A	05-02-1988
			DE 3775102 D1	23-01-1993
			EP 0243956 A2	04-11-1993
			ES 2038136 T3	16-07-1995
EP 0659787	A	28-06-1995	KR 9003415 B1	18-05-1990
			EP 0659787 A1	28-06-1995
			AT 196483 T	15-10-2000
			AU 684573 B2	18-12-1997
			AU 8161894 A	29-06-1995
			BR 9405195 A	01-08-1995
			CA 2138676 A1	24-06-1995
			CN 1106418 A , B	09-08-1995
			DE 69425949 D1	26-10-2000
			DE 69425949 T2	12-04-2001
			FI 946002 A	24-06-1995
			JP 7206954 A	08-08-1995
			NO 944968 A	26-06-1995